



TEST REPORT

DATE: 05-23-2017

Page 1 of 1

TEST NUMBER: 0237474

CLIENT	Newspec Carpet (Ning Bo)Co., Ltd.
---------------	-----------------------------------

TEST METHOD CONDUCTED	ASTM D7570 (Edge Curl) Standard Test Method for Evaluating Dimensional Stability of Pile Yarn Floor Covering
------------------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	PVC Backing Nylon
CONSTRUCTION	Multi-Level Loop Pile
BACKING	Thermoplastic

GENERAL PRINCIPLE

This test is designed to examine dimensional changes in textile floor coverings due to various conditions of heat and moisture. Measurements are taken in the length and cross directions of the test sample after each treatment. A change in the dimension of the test sample is calculated as a percentage of the original preconditioned sample measurement. Shrinkage is indicated by a negative quotation while expansion is indicated by a positive quotation.

TEST RESULTS

	Measurement	Percent	Edge Curl		Measurement	Percent
M₀	19.6915	-----	0.02 Inch	C₀	19.6945	-----
M_{T1}	19.6815	-0.051 %	0.04 Inch	C_{T1}	19.7015	+0.036 %
M_{T2}	19.6785	-0.066 %	0.08 Inch	C_{T2}	19.6945	+0.000 %
M_{T3}	19.6755	-0.081 %	0.13 Inch	C_{T3}	19.6960	+0.008 %
M_{T4}	19.6775	-0.071 %	0.08 Inch	C_{T4}	19.6915	-0.015 %

M₀	Original measurement in machine direction
C₀	Original measurement in cross direction
T₁	Two hours in drying oven at 60° C
T₂	Two hours submerged in 0.1% detergent solution at 20°C
T₃	Twenty four hours in drying oven at 60°C
T₄	Forty eight hours conditioning at 20°C and 65% relative humidity

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.